

## BERCROM CTD

CHROME/TANNIN

### CHEMICAL COMPOSITION

Basic chrome sulphate and phenolic tannin without formaldehyde

### CHARACTERISTICS

<i>Appearance:</i>	<i>fine, green powder</i>
<i>pH in solution at 10%:</i>	<i>2,5 - 3,5</i>
<i>Chrome content:</i>	<i>16 - 18%</i>

### PROPERTIES

**BERCROM CTD** is used to obtain soft and clear hides for chrome retanning and for the pretanning of chrome or vegetable tanned hides.

**BERCROM CTD** thanks to its good resistance to light is used for the retanning of white or pastel coloured leather.

**BERCROM CTD** is also used for the retanning of double faced ram skins where it improves the softness and the velours of the treated hides.

### CONTINUE

Our suggestions for the use of the products correspond to our present knowledge. They do not release the purchaser in any way whatsoever from the responsibility of carrying out their own tests to establish the suitability of the products supplied in relation to the results that are to be obtained. The usage methods of the products are not within our control and therefore become the complete responsibility of the purchaser. We guarantee the quality of our products in respect of the general sales and supply terms and conditions.

## USAGE METHOD

Use 4 - 6% of the shaved weight for retanning soft hides with a thickness of 1,8 - 2 mm.

Use 4 - 6% of the shaved weight for retanning hides for soft shoe uppers with a thickness of 1,4 - 1,6 mm.

Use 3 - 4% of the dry weight for retanning double faced ram skins.