

BERFAT DH

COMPLETE FATLIQUOR FOR LEATHERS

CHEMICAL COMPOSITION

Blend of fat natural and synthetic substances

CHARACTERISTICS

<i>Appearance:</i>	<i>oily red/brown-coloured</i>
<i>Fatty matter content:</i>	<i>55 – 60%</i>
<i>pH emulsion at 10%:</i>	<i>7 – 8</i>
<i>Light fastness:</i>	<i>good</i>
<i>Ionic charge:</i>	<i>anionic</i>
<i>Storage:</i>	<i>6 months in normal conditions</i>
<i>Chrome stability:</i>	<i>yes</i>
<i>Electrolyte stability:</i>	<i>yes</i>

CONTINUE

Our suggestions for the use of the products correspond to our present knowledge. They do not release the purchaser in any way whatsoever from the responsibility of carrying out their own tests to establish the suitability of the products supplied in relation to the results that are to be obtained. The usage methods of the products are not within our control and therefore become the complete responsibility of the purchaser. We guarantee the quality of our products in respect of the general sales and supply terms and conditions.

PROPERTIES

Special product of anionic kind, liquid, limpid at 5-10° C, and forms stable transparent emulsions with water.

It is expressly indicated to fatliquor chrome, vegetable or synthetic-tanned skins, especially to fatliquor gloves and garment skins, thanks to its action studied to favour maximum softness.

It can be indifferently used in float or dry, without losing its characteristics of softness, hand and extremely pleasant surface touch. It contains a high percentage of fatty substances and gives very fine, and very stable emulsions.

The product penetrates deeply in the dermal fibres and gives the skins a sweet and soft touch, favouring writing on the surface.

It has good light and ageing fastness, favours dyeing evenness and causes no fatty exudations even if plate drying is perfect.

It is recommended for all soft, garment and glove articles, in aqueous float or dry, for buffed and full grain.

USAGE METHOD

No special attention is required in preparing the emulsion, this operation can be carried out very easily even with cold water.

The use temperature can vary from 30° and 70°C.

The usage quantities, depending on the article to be manufactured, range between 2% and 10%.