

231

## ELCATAN DDS 100

SYNTHETIC TANNIN FOR WHITE LIGHT

## CHEMICAL COMPOSITION

dihydroxy-diphenyl-sulphone

CHARACTERISTICS	
Appearance:	white powder
pH in solution at 10%:	3,5 – 4,5

## PROPERTIES

**ELCATAN DDS 100** gives leather with soft and round touch with firm grain when used in retanning on chrome.

It is particularly indicated for retanning of soft leather like nappa for shoes, nappa for garments etc. from all type of leathers like bovine, sheep etc. It is recommended to use from 2 to 8% according to the type of leather and softness desired. **ELCATAN DDS 100** is recommended for retanning of leather for automotive industry and soft upholstery for house halls.

It has a good whitening property and Is adequate for retanning of materials for light and pastel colours. **ELCATAN DDS 100** can be used in retanning, in combination with vegetable tanning agents and resins, giving very good fullness and roundess, both for full grain leathers, pure aniline, and for corrected grain: in this case 2 to 4% is recommended.

**ELCATAN DDS 100** could be used as a pre-tanning before chrome tanning of sheep, improving fullness in the most empty areas of leather, without giving excessive firmness to the finished leathers. In this case 3 to 5% is recommended on pickled weight.

Our suggestions for the use of the products correspond to our present knowledge. They do not release the purchaser in any way whatsoever from the responsibility of carrying out their own tests to establish the suitability of the products applied in relation to the results that are to be obtained. The usage methods of the products are not within our control and therefore become the complete nesponsibility of the purchaser. We guarantee the quality of our products in respect of the general sales and supply terms and conditions.