

## RESIFILL 540

### RETANNING RESIN

#### CHEMICAL COMPOSITION

Acrylic polymer with a high molecular weight

#### CHARACTERISTICS

<i>Appearance:</i>	<i>white viscous liquid</i>
<i>pH in solution at 10%:</i>	<i>6 – 7</i>
<i>Solubility:</i>	<i>100% in water</i>
<i>Compatibility:</i>	<i>with chrome salts, zircon, vegetable and synthetic tannins</i>
<i>Solidity to light:</i>	<i>optimum</i>

#### PROPERTIES

**RESIFILL 540** can be used in all phases of retanning thereby obtaining an optimum filling with firmness of the grain. The best results are obtained if **RESIFILL 540** is used after chrome tanning and before neutralisation.

**RESIFILL 540** is used to obtain a real Italian nappa, in combination with synthetic or vegetable tannins and thereby obtaining various forms of softness and fullness.

Using **RESIFILL 540** obtains full grain and correct grain finishing.

#### USAGE METHOD

2 - 6% on the shaved weight is used, depending on the type of hide and according to the effect required.