

## RESIFILL 730

RETANNING RESIN

### CHEMICAL COMPOSITION

Concentrated acrylic polymer

#### CHARACTERISTICS

<i>Appearance:</i>	<i>viscous, colourless liquid</i>
<i>Ionic charge:</i>	<i>anionic</i>
<i>pH in solution at 10%:</i>	<i>6,5 – 7,5</i>
<i>Solubility:</i>	<i>complete in water</i>
<i>Concentration:</i>	<i>25 – 30%</i>
<i>Compatibility:</i>	<i>with syntans, natural tannins, polyacrylates, sulphonated and sulphited oils.</i>
<i>Storage:</i>	<i>6 months in normal conditions.</i>

#### PROPERTIES

**RESIFILL 730** can be used alone or in combination with synthetic and natural tannins, which are added to the same float.

**RESIFILL 730** provides leathers with firm grain and exceptional full and round touch.

Use percentages range from 2 to 5% on shaved weight, depending on leather type and their thickness.

It is also used in the end, after fatliquoring, to obtain the maximum effects.