

RESIFILL GT25

RETANNING AUXILIARY

CHEMICAL COMPOSITION

Glutar-dialdehyde in aqueous solution

CHARACTERISTICS

<i>Appearance:</i>	<i>colourless liquid</i>
<i>Active matter:</i>	<i>20 – 25%</i>
<i>pH in pure solution:</i>	<i>3 - 4</i>

PROPERTIES

RESIFILL GT25 is an aqueous solution of glutar-dialdehyde that, for its particular tanning properties, is a product for various use. It has softening and fulling action and does not make the leathers heavy, making them more precious.

RESIFILL GT25 is stable in the PH range below 9; stronger alkaline reactions and in particular high temperatures give place to polymerization.

RESIFILL GT25 is compatible with mineral tanning agent, pickling acids and neutral salts, in any ratio of blend and concentration.

RESIFILL GT25 has good tanning properties in a wide range of ph. The astringent power gets stronger increasing bath alkalinity. Tanning float good exhaustion is obtained by setting ph at 5 - 6 and by using short ratios and quite high temperatures.

USAGE METHOD

In general, the percentage of **RESIFILL GT25** used in pretanning is 1,5 - 3% referred to pelt weight; we recommend to add the tanning agent in water dilution (1:2), in 2 - 3 parts in case of large amounts.